

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 0 854 157 A1**

(12)

# EUROPEAN PATENT APPLICATION

(43) Date of publication:  
22.07.1998 Bulletin 1998/30

(51) Int Cl.<sup>6</sup> C08F 290/06, B29C 37/00,  
C08G 18/67, C09D 175/16

(21) Application number: 98300272.6

(22) Date of filing: 15.01.1998

(84) Designated Contracting States:  
AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC  
NL PT SE  
Designated Extension States:  
AL LT LV MK RO SI

- Cobblestick, David S.  
Kent, Ohio 44240 (US)
- Shanoski, Henry  
Akron, Ohio 44333 (US)
- Sullivan, Brian J.  
Mogadore, Ohio 44260 (US)

(30) Priority: 17.01.1997 US 785514

(71) Applicant: GENCORP INC:  
Fairlawn, Ohio 44333-3300 (US)

(74) Representative: Stoner, Gerard Patrick  
MEWBURN ELLIS  
York House  
23 Kingsway  
London WC2B 6HP (GB)

(72) Inventors:  
• McBain, Douglas S.  
Norton, Ohio 44203 (US)

(54) **In-mold coating compositions, their preparation and use**

(57) An in-mold coating composition for a fiber reinforced plastic comprises an aliphatic resin such as a saturated aliphatic ester intermediate polyurethane having terminal acrylate end groups, a saturated (cyclo)aliphatic (meth)acrylate such as isobornyl acrylate, a hydroxyl alkyl (meth)acrylate, a polyacrylate ester of an alkylene polyol, and a vinyl substituted aromatic. The in-mold

coating compositions have good end use weather-resistant properties so that there is no need for a subsequent paint coat thereon which heretofore has been required. The paint-free coating compositions can be either clear or pigmented and can contain various additives such as lubricants, adhesion aids, hardeners, and the like.

**EP 0 854 157 A1**